



## TECHNICAL SHEET ART. NICE



Class: S1P SRC  
 Sizes: 38-48  
 Instep: 12  
 Weight(±10%): 526 gr. (\*)

**Description** Sandal in micro fiber , black color , 100% polyester lining, Non-Metallic HRP Insole , Light & Soft Insole antistatic and breathable , polyurethane sole , bending resistant , abrasion resistant, oil resistant , slip resistant , antistatic , with the "little pad" SOFT WALK inside.

**Plus** toe protection PRO CAP

**Suggested sectors of usage** Building/Construction , Servicing, Mechanical Industry, Cooperative Society

**Care and Maintenance** clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source

Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
<b>Toe Cap</b> : Top Composite toe cap, impact resistant 200 J	5.3.2.3 5.3.2.4	Impact resistance Compression resistance	mm mm	14,0 16,0	>= 14 >= 14
<b>Midsole:</b> non metallic HRP Insole with high tenacity fibers layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100	>= 1.100
<b>Antistatic footwear:</b> dissipation capacity of the electrostatic charge	6.2.2.2	Electric resistance - Wet - Dry	Mohm Mohm	5,29 8,88	>= 0,1 <= 1000
<b>Capacity of Energy Absorption in the heel area</b>	6.2.4	Energy absorption in the heel area	J	36	>= 20
<b>Upper:</b> Microfiber, black color, thickness 1,8 mm	5.4.6 5.4.3	Water vapour permeability Coefficient of permeability Tearing Strength	mg/cmq h mg/cmq N	2,5 22,0 85	>= 0,8 >= 15 >= 60
<b>Vamp Lining:</b> non woven textile for toe cap, grey color	5.5.3 5.5.1 5.5.2	Water vapour permeability Coefficient of permeability Tearing Strength Abrasion resistance (dry) Abrasion resistance (wet)	mg/cmq h mg/cmq N cycles cycles	3,4 30,2 30 no rupture no rupture	>= 2 >= 20 >= 15 25.600 12.800
<b>Quarter lining:</b> 100% honeycomb finished polyester, breathable, abrasion resistant, grey colour	5.5.3 5.5.1 5.5.2	Water vapour permeability Coefficient of permeability Tearing Strength Abrasion resistance (dry) Abrasion resistance (wet)	mg/cmq h mg/cmq N cycles cycles	6,8 54,4 25 no rupture no rupture	>= 2 >= 20 >= 15 51.200 25.600
<b>Insole lining:</b> textile anti perforation midsole HRP Insole	5.7.3	Water Absorption Ability to release water	Mg/cm <sup>2</sup>	82 97%	>= 70 >= 80%
<b>Sole:</b> polyurethane, bending resistant, abrasion resistant, oil resistant, slip resistant, antistatic, with high damping capacity thanks to the little pad SOFT WALK inserted inside	5.8.2 5.8.3 5.8.4 5.8.5 6.4.2 5.11	Tearing Strength Abrasion resistance Bending resistance Hydrolysis Hydrocarbons resistance (volume increase) Slip resistance on ceramic floor with water and detergent Slip resistance on steel floor with glycerine	kN/m mm <sup>3</sup> mm mm % flat inclined flat inclined	5,9 154 2,5 1,0 0,2% 0,54 0,46 0,25 0,22	>= 5 <= 250 <= 4 <= 6 <= 12% >= 0,32 >= 0,28 >= 0,18 >= 0,13

Azo dye free: no presence of azo dye forbidden by normative 1907/2006/CE Attachment XVII (method UNI EN 14362-1:2012 + 14362-3:2012 Textile)

(\*) = Indicative weight that refers to 1/2 pair in size 42